

This website uses cookies to improve the user's experience during working with our network and to provide users with dedicated services and functions. By further use you agree with that.OKDetails

Address	Cyclotec Leotec Group Shotlandskaya st. 8 St. Petersburg, 198035
Country	Russian Federation

PRODUCTS OR MACHINERY

Our mill designed to be multi purpose (both for wet & dry) continuous ultra fine grinding of super hard materials of mineral & ceramic origin.

1. The feed fraction is minus 5 millimeter

Quartz sands feed fraction:

SIZE mm / CONTENT %

-5 +3 / 6,24

-3 +2 / 24,14

-2 +1 / 15,52

-1 +0,63 / 28,36

-0,63 +0,315 / 23,02

-0,315 / 2,7

Engine capacity 37 kW, classifier 2.2 kW, fan 7.5 kW

2. We have a poor classifier which is much inferior to the abilities of the PCM so we run it without classifier too, to demonstrate its abilities (it has classification ability of 20 micron & cannot classify 5 microns fraction effectively and it limits our research capabilities).

ZrO₂-15-11 –zirconia milling, feed fraction 300 micron at rate of 500 kg/hour, open circuit - WITHOUT CLASSIFICATION

Please see that 62% are minus 5 micron & 23% are less then one micron(fifth column from the left--- accumulative frequency).

Any way we are not aware of a classifier which could efficiently classify large volume d100 4 micron, if we had this classifier then we would have fulfilled Requirement indicators of d50 0.75 micron.

Another possibility is to convert our mill from continuous action to Periodic action, we are certain the results would be in nano range but then production capacity would drop to 100-200 kg/h.

3. As you would learn from the material you received we can do d97 5 micron and better.

4. We can grind finer then 5 microns. We are working on optimization of grinding media size versus energy consumption. Grinding media size is D(av) 12-14 mm.

5. Energy consumption for quartz sand for d97 is:

5 microns max. 190 kWh/t

10 microns max. 135 kWh/t

20 microns max. 89 kWh/t

30 microns max. 69 kWh/t

With improvements in the classifier the energy consumption would be lower. Liner wear would be approximately 0.1 kg/ton milled product (depending on the hardness of the material).

7. The next stage modifications would be with 10, 15, 25 ton/h capacity.

The larger the model would be the bigger the feed fraction it could intake up to 50-70 millimeters! We are certain our model, know how & calculations withstand this range of production capacity, For mill with capacity more then 25 ton/h we have to change concept so it needs more research in order to give guarantees but we are planning 50 ton/hour AG mill.

Definitions:

Open circuit is : the mill is charged feed fraction sized less then 5 mm(see in the file "capabilities of PCM.doc.") with different feed speed(kg/hour).

Classifier & cyclone are not used. The grinded product is going to tank.

Results of those tests shown in graphs 4,5,6,7,8 in the file "capabilities of PCM.doc."

Closed circuit is: grinding in PCM with defined capacity, classifying the material by bigger then 20 microns & smaller then 20 microns. The coarse product goes back to mill, fines go to cyclone & filter. Capabilities by capacity are defined by fan and it is 250 kg/hour of feed product. Efficiency of classification is defined by the poor design of our classifier. In coarse powder there is till 50 % of fines see graph 2 in the file "capabilities of PCM.doc."

Company Profile of **Cyclotec**

A service of glasssglobal.com, an affiliate of glasssglobal group.

The address material you printed out is copyright and belongs to the Company or to its third party Marketing Agency, and all rights are reserved. Any User who accesses such material may do so only for its own personal use, and the use of such material is at the sole risk of the User. Redistribution or other commercial exploitation of such address material is expressly prohibited. Where such address material is provided by a third party, each User agrees to observe and be bound by the specific terms of use applying to such news material. Glass Global does not represent or endorse the accuracy or reliability of any of the info contained in any address or external websites referred to in this printout.www.glasssglobal.com - The International Portal to the Glass Industry - OGIS GmbH