

This website uses cookies to improve the user's experience during working with our network and to provide users with dedicated services and functions. By further use you agree with that.OKDetails

Address	UWM Mineral processing 28 Heinitzburg Street, Windhoek 1666 Windhoek
Country	Namibia
State	Washington

PRODUCTS OR MACHINERY

Low Iron Dolomite -1mm:

CHEMICAL ANALYSIS(%)

%CaO--31.33
%MgO--21.14
%Fe2O3--0.04
%Al2O3--<0.06
%SiO2--0.93
%K2O--<0.06
%SO3--<0.05
% L.O.I--46.04

PHYSICAL PROPERTIES

pH--9.35 – 9.8
Moisture--< 0.5 %
Oil Absorption--13 - 15g per 100g
Refractive Index--1.62
Hardness moh--3.5
Whiteness SABS 137 Dry--86-88
Specific Gravity--2.85 – 2.87
Bulk density (loose) --1.68g/ml

PARTICLE SIZING

NORM
Screen (micron - µm)
Avg % retained
2800--0.00
2000--0.00
1180--0.05
425--28.69
125--57.74
90-- 6.47
PAN--7.04
Total --100.00

Company Profile of **UWM Mineral processing**

A service of glasssglobal.com, an affiliate of glasssglobal group.

The address material you printed out is copyright and belongs to the Company or to its third party Marketing Agency, and all rights are reserved. Any User who accesses such material may do so only for its own personal use, and the use of such material is at the sole risk of the User. Redistribution or other commercial exploitation of such address material is expressly prohibited. Where such address material is provided by a third party, each User agrees to observe and be bound by the specific terms of use applying to such news material. Glass Global does not represent or endorse the accuracy or reliability of any of the info contained in any address or external websites referred to in this printout.www.glasssglobal.com - The International Portal to the Glass Industry - OGIS GmbH